General information


Client name	Shandong glass tech industrial co.,Ltd
Client address	No 63, haier road, qingdao 266000 Shandong CN
Measurement date	2026-03-03
Laboratory	WUR LightLab
Operator	bb
Measuring equipment	Haze (HazeGard i ISSA (Hortiscatter)
Measurement conditions	The measurements have been carried out at an ambient temperature of 15-25°C and a relative air humidity of 40-60%.
Report made by	bb
Report controlled by	vm

Sample information

Client ID	*WUR ID*	*Size [mm]*	*Remarks*
Semi low iron diffused 2 AR coating	SHT26B	500 x 500 x 4	
Normal diffused 2AR coating	SHT26C	500 x 500 x 4	


Sample preparation Conform NEN 2675+C1

Measurements are carried out on the samples provided by the Client as described above. It is the responsibility of the client to select representative samples from a batch.
Measurements are carried out on a randomly chosen spot on the sample as indicated below. It is the responsibility of the Client to provide uniform samples.



Test results

	Haze [%]	Hortiscatter [%]
Method	ASTMD-1003	NEN2675
Uncertainty	*±5%*	*±5%*
Semi low iron diffused 2 AR coating	69	58
Normal diffused 2AR coating	40	40



WUR LightLab
Stichting Wageningen Research, Wageningen Plant Research, WUR LightLab
WUR Klima (building number 109)
Bornsesteeg 48
6708 PE Wageningen
The Netherlands
Email: lightlab@wur.nl

DISCLAIMER
© 2026 Wageningen, Foundation Stichting Wageningen Research (WR), research institute Wageningen Plant Research. All rights reserved. No part of this publication may be reproduced, stored in a retrieval system, or transmitted in any form or by any means, electronic, mechanical, photocopying, recording or otherwise, without the prior written permission of WR, research institute Wageningen Plant Research, WUR LightLab.
The Foundation WR is not responsible for any damage caused by using the content of this report.